


## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>A61B 17/12</b>	<b>A1</b>	(11) International Publication Number: <b>WO 99/65401</b> (43) International Publication Date: 23 December 1999 (23.12.99)
<p>(21) International Application Number: PCT/US99/13493</p> <p>(22) International Filing Date: 16 June 1999 (16.06.99)</p> <p>(30) Priority Data: 09/100,426 18 June 1998 (18.06.98) US</p> <p>(71) Applicant: SCIMED LIFE SYSTEMS, INC. [US/US]; One Scimed Place, Maple Grove, MN 55311-1566 (US).</p> <p>(72) Inventors: EDER, Joseph, C.; 23423 Toyonta Road, Los Altos Hills, CA 94024 (US). OLSON, Stanley, W., Jr.; 6419 Copper Creek Drive, Dallas, TX 75248 (US). SLAIKEU, Paul, C.; 3594 Skyline Drive, Hayward, CA 94542 (US). ABRAMS, Robert, M.; 359 Redondo Terrace, Sunnyvale, CA 94086 (US).</p> <p>(74) Agents: WHELOCK, E., Thomas et al.; Morrison &amp; Foerster LLP, 755 Page Mill Road, Palo Alto, CA 94304-1018 (US).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>
(54) Title: WATER-SOLUBLE COATING FOR BIOACTIVE VASO-OCCLUSIVE DEVICES		
		
<p>(57) Abstract</p> <p>A vaso-occlusive device having a bioactive inner coating and a water-soluble outer coating. Methods of preparing the devices are also provided.</p>		

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## WATER-SOLUBLE COATING FOR BIOACTIVE VASOOCCLUSIVE DEVICES

### FIELD OF THE INVENTION

5           This invention relates to a medical device for forming an embolism within the vasculature of a patient. More particularly, it concerns an occlusion device having an outer coating of a dissolvable, water-soluble agent over an inner coating of a bioactive agent.

### BACKGROUND

10           Vaso-occlusive devices are surgical implements that are placed within open sites in the vasculature of the human body. The devices are introduced typically via a catheter to the site within the vasculature that is to be closed. That site may be within the lumen of a blood vessel or perhaps within an aneurysm stemming from a blood vessel.

15           There are a variety of materials and devices which have been used to create such emboli. For instance, injectable fluids such as microfibrillar collagen, various polymeric foams and beads have also been used. Polymeric resins, particularly cyanoacrylate resins, have been used as injectable vaso-occlusive materials. Both the injectable gel and resin materials are typically mixed with a radio-opaque material to allow accurate siting of the resulted material. There are significant risks involved in use of a cyanoacrylates, because  
20           of the potential for misplacement. Such a misplacement would create emboli in undesired areas. Cyanoacrylate resins or glues are somewhat difficult, if not impossible, to retrieve once they are improperly placed.

          Other available vaso-occlusive devices include mechanical vaso-occlusive devices. Examples of such devices are helically wound coils and braids. Various shaped coils have  
25           been described. For example, U.S. Patent No. 5,624,461 to Mariant describes a three-dimensional in-filling vaso-occlusive coil. U.S. Patent No. 5,639,277 to Mariant et al. describe embolic coils having twisted helical shapes and U.S. Patent No. 5,649,949 to Wallace et al. describes variable cross-section conical vaso-occlusive coils. A random shape is described, as well. U.S. Patent No. 5,648,082 to Sung et al., describes methods for  
30           treating arrhythmia using coils which assume random configurations upon deployment from a catheter. U.S. Patent No. 5,537,338 to describes a multi-element intravascular occlusion device in which shaped coils may be employed. Spherical shaped occlusive

devices are described in U.S. Patent No. 5,645,558 to Horton. Horton describes how one or more strands can be wound to form a substantially hollow spherical or ovoid shape when deployed in a vessel. U.S. Patent Application 07/978,320, filed November 18, 1992, entitled "Ultrasoft Embolization Coils with Fluid-Like Properties" by Berenstein et al., is  
5 found a coil having little or no shape after introduction into the vascular space.

There are a variety of ways of discharging shaped coils and linear coils into the human vasculature. In addition to those patents which apparently describe only the physical pushing of a coil out into the vasculature (e.g., Ritchart et al.), there are a number of other ways to release the coil at a specifically chosen time and site. U.S. Patent No.  
10 5,354,295 and its parent, 5,122,136, both to Guglielmi et al., describe an electrolytically detachable embolic device.

A variety of mechanically detachable devices are also known. For instance, U.S. Patent No. 5,234,437, to Sepetka, shows a method of unscrewing a helically wound coil from a pusher having interlocking surfaces. U.S. Patent No. 5,250,071, to Palermo, shows  
15 an embolic coil assembly using interlocking clasps mounted both on the pusher and on the embolic coil. U.S. Patent No. 5,261,916, to Engelson, shows a detachable pusher-vaso-occlusive coil assembly having an interlocking ball and keyway-type coupling. U.S. Patent No. 5,304,195, to Twyford et al., shows a pusher-vaso-occlusive coil assembly having an affixed, proximally extending wire carrying a ball on its proximal end and a pusher having  
20 a similar end. The two ends are interlocked and disengage when expelled from the distal tip of the catheter. U.S. Patent No. 5,312,415, to Palermo, also shows a method for discharging numerous coils from a single pusher by use of a guidewire which has a section capable of interconnecting with the interior of the helically wound coil. U.S. Patent No. 5,350,397, to Palermo et al., shows a pusher having a throat at its distal end and a pusher  
25 through its axis. The pusher sheath will hold onto the end of an embolic coil and will then be released upon pushing the axially placed pusher wire against the member found on the proximal end of the vaso-occlusive coil.

In addition, several patents describe deployable vaso-occlusive devices that have added materials designed to increase their thrombogenicity. For example, fibered vaso-  
30 occlusive devices have been described at a variety of patents assigned to Target Therapeutics, Inc., of Fremont, California. Such vaso-occlusive coils having attached fibers is shown in U.S. Patent Nos. 5,226,911 and 5,304,194, both to Chee et al. Another

vaso-occlusive coil having attached fibrous materials is found in U.S. Patent No. 5,382,259, to Phelps et al. The Phelps et al. patent describes a vaso-occlusive coil which is covered with a polymeric fibrous braid on its exterior surface. U.S. Patent No. 5,658,308 to Snyder is directed to a coil having a bioactive core.

5           In other attempts to increase thrombogenesis, vaso-occlusive coils have also been treated with variety of substances. For instance, U.S. Patent No. 4,994,069, to Ritchart et al., describes a vaso-occlusive coil that assumes a linear helical configuration when stretched and a folded, convoluted configuration when relaxed. The stretched condition is used in placing the coil at the desired site (by its passage through the catheter) and the coil  
10           assumes a relaxed configuration -- which is better suited to occlude the vessel -- once the device is so placed. Ritchart et al. describes a variety of shapes. The secondary shapes of the disclosed coils include "flower" shapes and double vortices. The coils may be coated with agarose, collagen or sugar.

          U.S. Patent No. 5,669,931 to Kupiecki discloses coils that may be filed or coated  
15           with thrombotic or medicinal material. U.S. Patent No. 5,749,894 to Engleson discloses polymer coated vaso-occlusion devices. U.S. patent No. 5,690,671 to McGurk discloses an embolic element which may include a coating, such as collagen, on the filament surface.

          U.S. Patent No. 5,536,274 to Neuss shows a spiral implant which may assume a variety of secondary shapes. Some complex shapes can be formed by interconnecting two  
20           or more of the spiral-shaped implants. To promote blood coagulation, the implants may be coated with metal particles, silicone, PTFE, rubber latices, or polymers.

          None of the above documents address the complications of deploying devices with a bioactive coating, such as one which increases thrombogenicity. Of the patents which disclose implantable stents which are treated so as to retard deposition of unwanted  
25           materials (see *e.g.*, U.S. Patent No. 5,147,370 to McNamara et al. and U.S. Patent No. 5,383,928 to Scott et al.), the treated devices are not vaso-occlusive coils and, in addition, these anti-thrombotic components are generally permanently bound to the stents.

          In addition, these devices do not contain an inner, bioactive coating which is generally permanently bonded or attached to the device. Although these bioactive coatings  
30           provide therapeutics or increase thrombogenicity of vaso-occlusive devices *in vivo*, the inner coating may induce complications during coil packing and coil manipulation. None

of the documents discussed above make any suggestion of treating vaso-occlusive coils with a dissolvable outer coating over a bioactive inner coating.

### SUMMARY OF THE INVENTION

5 In one aspect, the present invention provides a vaso-occlusive device comprising: a) a biocompatible metal vaso-occlusive member; b) an inner bioactive coating on said vaso-occlusive member; and c) an outer coating on said inner coating, said outer comprising a water-soluble agent. The vaso-occlusive member may be a coil, a sphere, or other shaped structure. In one preferred embodiment, the vaso-occlusive member is an elongated helical  
10 coil comprises of a series of axial windings, for instance a cylindrical helical coil. Preferably, the coil is made of gold, rhenium, platinum, palladium, rhodium, ruthenium, stainless steel, tungsten and alloys thereof.

The inner bioactive coating may be any active substance, for example, a thrombogenic agent that promotes healing, or another therapeutic agent. Preferably, the  
15 inner coating is permanently bonded to said vaso-occlusive member. The inner coating can be collagen, fibrinogen, growth factors and synthetic peptides. The inner coating may also be deposited on the member by plasma treatment.

The dissolvable outer coating can be an anti-thrombogenic agent, a therapeutic agent or an agent which reduces friction during delivery. In one preferred embodiment, the  
20 outer coating is acetyl salicylic acid (aspirin), heparin, tissue plasminogen activator (TPA), streptokinase, urokinase, hirudin, coumadin or alnert. In yet another embodiment, the outer coating further includes a component that affects the solubility of said outer coating. This component can be made part of the outer coating before deposition on the member or, alternatively, can be deposited as an overcoating over the outer coating. In one preferred  
25 embodiment, the water-soluble, anti-thrombotic outer coating dissolves shortly after said vaso-occlusive member is deployed. Preferably, the inner and outer coatings do not affect the shape of said vaso-occlusive member after deployment.

In another aspect, the invention provides a method for treating a vaso-occlusive device comprising (a) providing an inner coating for a vaso-occlusive device comprising a  
30 bioactive material; and (b) providing an outer coating over said inner coating, said outer coating comprising a dissolvable water-soluble material. In one embodiment, the vaso-occlusive device comprises a metallic element, for instance a helically wound coil. The

coil may be made from gold, rhenium, platinum, palladium, rhodium, ruthenium, stainless steel, tungsten and alloys thereof.

Preferably, the inner coating is thrombogenic and is permanently bonded to the vaso-occlusive member and may be collagen, fibrinogen, vitronectin, a growth factor or a synthetic peptide. The inner coating may also be created by plasma treatment of the vaso-occlusive member. The outer coating is preferably anti-thrombogenic, for example, acetyl salicylic acid (aspirin), heparin, coumadin or alnert. Optionally, the outer coating contains a component such as a lipid (phosphatidyl choline) or hydrophilic compound (*e.g.*, polyvinyl alcohol). The optional component may affect the rate at which the outer coating dissolves.

In yet another aspect, the present invention provides a produced by the methods described herein.

As will become apparent, preferred features and characteristics of one aspect of the invention are applicable to any other aspect of the invention.

#### BRIEF DESCRIPTION OF THE DRAWINGS

In the drawings, which are not to scale:

Figure 1 is a perspective view of one embodiment of the invention.

Figure 2 is a perspective view of another embodiment of the invention showing a coil having a permanently bonded inner coating and a water-soluble, dissolvable outer coating.

#### MODES FOR CARRYING OUT THE INVENTION

The present invention provides a vaso-occlusive device having an outer coating of dissolvable, water-soluble agent. This dissolvable agent performs "temporary" functions, for example when the coating is an anti-thrombogenic agent, it reduces the likelihood of thrombus formation on the vaso-occlusive device or in the aneurysm during the delivery process. Other suitable water-soluble outer coatings include agents which reduce friction or pharmaceutical agents.

In one aspect, the outer, anti-thrombotic coating is placed over an inner coating of a bioactive agent. The term "bioactive" refers to any agent which exhibits effects *in vivo*, for example an thrombotic agent, a therapeutic agent or the like. The terms "thrombotic" and

“thrombogenicity” are used to refer to any substance which increases or promotes adhesion of any of the components of blood and/or plasma, including but not limited to, blood cells, platelets, and other blood-borne components. Preferably, the inner coating is permanently bonded to the coil, while the outer coating is designed to dissolve shortly after coil deployment so that the underlying material can safely perform its intended purpose, *i.e.* being the healing cascade within the vessel. The outer coating may be water soluble, anti-thrombotic, anticoagulant or antiplatelet material of any type. The outer coating may be dip or spray coated, wiped onto the coil or attached by other means such as vapor deposition. Other methods will be known to those in the art.

Figures 1 and 2 show typical vaso-occlusive devices suitable for use with this procedure. Figure 1 shows a typical vaso-occlusive device (100). Vaso-occlusive device (100) is shown in Figure 1 to comprise a helically wound coil (102) having tips (104) to ease the potential of the component wire to cause trauma in a blood vessel. The device may include tufts or fiber bundles attached to it, so to increase the amount and volume of fiber held by the coil and thereby to promote overall thrombogenicity of the device. Typical of a vaso-occlusive device comprising a helical coil having attached fibrous elements such as shown in Figure 1 is found in U.S. Patent No. 5,226,911 to Chee et al, the entirety of which is incorporated by reference.

Figure 2 shows a vaso-occlusive device (200) comprising a helically wound coil (202), an inner coating (204) and an outer coating (206). The inner coating is generally a substance which is permanently bound to the coil (202) and which increase thrombogenicity of the coil.

The occlusion devices of the invention may be made using conventional equipment and procedures. For example, helical coils may be prepared by wrapping a suitable wire about a cylindrical or conical mandrel. The strand(s) are then placed axially through the core of the helix and, if a multiplicity of strands are employed, their ends bound by heat, adhesives, or mechanical means. Radial filaments may be attached to the windings of the helix by tying or with adhesives.

The polymeric materials used in the vaso-occlusive devices in Figures 1 and Figure 2 are known materials. They are those materials which are generally approved for use as implants in the body or could be so approved. They may be of polymers such as polyethylene, polyacrylics, polypropylene, polyvinylchloride, polyamides such as Nylon,



polyurethanes, polyvinylpyrrolidone, polyvinyl alcohols, polyvinylacetate, cellulose acetate, polystyrene, polytetrafluoroethylene, polyesters such as polyethylene terephthalate (Dacron), silk, cotton, and the like. When the polymers are fibrous, they are often looped or tufted as shown in the drawings. Although it is not critical to this invention, they are usually assembled in bundles of 5 to 100 fibers per bundle. Preferred materials for the polymer component of vaso-occlusive devices comprise polyesters, polyethers, polyamides, and polyfluorocarbons. Especially preferred is polyethyleneterephthalate, sold as Dacron.

The coils (102 in Figure 1 and 202 in Figure 2) may be made of any of a wide variety of biocompatible metals. In particular, the metals may be selected from gold, rhenium, platinum, palladium, rhodium, ruthenium, various stainless steels, tungsten, and alloys thereof. The preferred alloy is one comprising upwards of 90 percent platinum and at least a portion of the remainder, tungsten. This alloy exhibits excellent biocompatibility and yet has sufficient strength and ductility to be wound into coils of primary and secondary shape and will retain those shapes upon placement of the vaso-occlusive device in the human body. The diameter of the wire typically making up the coils is often in a range of 0.005 and 0.050 inches. The resulting primary coil diameter typically is in the range of 0.008 and 0.085 inches. Smaller coil diameters are used for finer problems and larger coil diameters and wire diameters are used in larger openings in the human body. A typical coil primary diameter is 0.015 and 0.018 inches. The axial length of a vaso-occlusive device may be between 0.5 and 100 centimeters. The coils are typically wound to have between 10 and 75 turns per centimeter.

In addition to the coils shown in the Figures, the vaso-occlusive device may comprise a substrate comprising a woven braid rather than the helical coil shown in those Figures. The vaso-occlusive device may comprise a mixture of coil and braid. Indeed, it is within the scope of this invention that a portion of the coil be polymeric, be a double winding mixture of metal and polymer, but in any event the vaso-occlusive device treated by a procedure of this invention must comprise a polymeric (natural or synthetic) fiber.

It is further within the scope of this invention that the vaso-occlusive device comprise shapes or structures other than coils or braids, for examples, solid sphere structures and the like.

In one aspect of the present invention, the vaso-occlusive devices described above and those similar to those specifically described above, are first treated with a coating of a bioactive coating and then subjected to treatment to provide a water-soluble material.

Preferably, neither the inner nor outer coatings interfere with the shape of the coil after deployment.

The outer coating may have one or more functions, including, but not limited to, reducing friction, providing a therapeutic for local or blood borne delivery, or reducing thrombosis, coagulation or platelet activity. Examples of suitable hydrophilic compounds include polyvinyl alcohol (PVA), polyvinylpyrrolidone (PVP), polyacrylamide and the like. Hydrophobic compounds include membrane lipids such as phosphatidyl choline, fatty acid esters and the like. Examples of water soluble therapeutics include thrombolytics such as tissue plasminogen activator (TPA), streptokinase, urokinase, hirudin and growth factors such as vEGF. Particularly preferred materials for anti-thrombogenic outer coatings include, but are not limited to, acetyl salicylic acid (aspirin), heparin, coumadin, alnert, along with esters or other derivatives of these compounds. The outer coating is designed to perform a temporary function, preferably during and immediately after delivery of the device. For example, an anti-thrombogenic outer coating reduces thrombus formation on the coil during delivery.

The outer coating preferably dissolves shortly after deployment of the device. The rate of dissolution may be controlled by using chemical bonding of various degrees to the substrate layer, or alternatively, by the addition of a third component which affects solubility. For example, hydrophilic substances such as polyvinyl alcohol or lipids such as phosphatidyl choline.

Treatment of vaso-occlusive coils with a water-soluble material can be carried out by any means known in the art, for example dip coating, spray coating, wiping, vapor deposition or the like.

The rate of dissolution of the outer coating may be controlled by using chemical bonding of various degrees to the substrate layer or by the addition of a third component that would affect the solubility of the outer layer. Non-limiting examples of these substances include hydrophilic compounds such as polyvinyl alcohol and lipids such as phosphatidyl choline. The solubility-affecting substances can be added as an overcoating

after the outer coating has been deposited on the coil or mixed into the outer coating before it is coated onto the vaso-occlusive device.

5 The inner, or bioactive coating or material is generally permanently bonded or attached to the coil. Preferably, the inner coating promotes cell attachment, more preferably it is thrombogenic. Non-limiting examples of bioactive coatings or materials which increase cell attachment and/or thrombogenicity include both natural and synthetic compounds, *e.g.*, collagen, fibrinogen, vitronectin, other plasma proteins, growth factors (*e.g.*, vascular endothelial growth factor, "vEGF"), synthetic peptides of these and other proteins having attached RGD (arginine-glycine-aspartic acid) residues, generally at one or  
10 both termini.

Another suitable thrombogenic bioactive coating involves "plasma treatment" of coils. (See, *e.g.*, co-pending USSN 08/598,325). These plasma-treated coils exhibit an amino-functionality which may be measured using known chemical methods. When the devices treated by this process are placed in a bloodstream, the amino-functionality results  
15 in a slight positive ionic charge on the surface of the fibers. This amino-functionality attracts platelets and thrombogenic proteins from the bloodstream. Plasma treatment may be carried out using *e.g.*, a plasma generator such as that found in U.S. Patent No. 3,847,652. The plasma may comprise a nitrogen containing gas, preferably those containing diatomic nitrogen or ammonia. Gas pressures are advantageously maintained at  
20 a very low level, *e.g.*, no greater than about 5 millimeters of mercury, preferably from 0.1 to 2 millimeters of mercury.

The period of time in which the vaso-occlusive device is subjected to the plasma need not be great. That is to say that for most applied power settings below about 200 watts and in the radio frequency region between 1 and 50 megahertz, the time of reaction  
25 need not be greater than 10 minutes to achieve the result described herein.

Other suitable bioactive inner coatings include therapeutic agents which act locally and/or are distributed *in vivo* by blood flow.

The devices which are treated according to the procedure of this invention are often introduced to a selected site using the procedure outlined below. This procedure may be  
30 used in treating a variety of maladies. For instance, in treatment of an aneurysm, the aneurysm itself may be filled with the devices made according to the procedure specified here. Shortly after the devices are placed within the aneurysm, the outer coating dissolves,

exposing the treated or untreated coil. An emboli begins to form and, at some later time, is at least partially replaced by collagenous material formed around the vaso-occlusive devices.

5 In general, a selected site is reached through the vascular system using a collection of specifically chosen catheters and guide wires. It is clear that should the aneurysm be in a remote site, e.g., in the brain, methods of reaching this site are somewhat limited. One widely accepted procedure is found in U.S. Patent No. 4,994,069 to Ritchart, et al. It utilizes a fine endovascular catheter such as is found in U.S. Patent No. 4,739,768, to Engelson. First of all, a large catheter is introduced through an entry site in the vasculature. 10 Typically, this would be through a femoral artery in the groin. Other entry sites sometimes chosen are found in the neck and are in general well known by physicians who practice this type of medicine. Once the introducer is in place, a guiding catheter is then used to provide a safe passageway from the entry site to a region near the site to be treated. For instance, in treating a site in the human brain, a guiding catheter would be chosen which would extend 15 from the entry site at the femoral artery, up through the large arteries extending to the heart, around the heart through the aortic arch, and downstream through one of the arteries extending from the upper side of the aorta. A guidewire and neurovascular catheter such as that described in the Engelson patent are then placed through the guiding catheter as a unit. Once the tip of the guidewire reaches the end of the guiding catheter, it is then extended 20 using fluoroscopy, by the physician to the site to be treated using the vaso-occlusive devices of this invention. During the trip between the treatment site and the guide catheter tip, the guidewire is advanced for a distance and the neurovascular catheter follows. Once both the distal tip of the neurovascular catheter and the guidewire have reached the treatment site, and the distal tip of that catheter is appropriately situated, e.g., within the 25 mouth of an aneurysm to be treated, the guidewire is then withdrawn. The neurovascular catheter then has an open lumen to the outside of the body. The devices of this invention are then pushed through the lumen to the treatment site. They are held in place variously because of their shape, size, or volume. These concepts are described in the Ritchart et al patent as well as others. Once the vaso-occlusive devices are situated in the vascular site, 30 the embolism forms.

Modifications of the procedure and device described above, and the methods of using them in keeping with this invention will be apparent to those having skill in this mechanical and surgical art. These variations are intended to be within the scope of the claims that follow.

5

CLAIMS

1. A vaso-occlusive device comprising:
  - a) a vaso-occlusive member;
  - b) an inner bioactive coating on said vaso-occlusive member; and
  - 5 c) an outer coating on said inner coating, said outer comprising a water-soluble agent.
- 10 2. The device of claim 1, wherein the vaso-occlusive member is a metallic element comprising an elongated helical coil .
3. The device of claim 2 wherein the coil is a cylindrical helical coil.
- 15 4. The device of claim 2 wherein the coil comprises a metal selected from gold, rhenium, platinum, palladium, rhodium, ruthenium, stainless steel, tungsten and alloys thereof.
- 20 5. The device of claim 1 wherein the inner bioactive coating is a thrombogenic or therapeutic agent.
6. The device of claim 5 wherein the inner bioactive coating is permanently bonded to said vaso-occlusive member.
- 25 7. The device of claim 6 wherein the inner bioactive coating is selected from the group consisting of collagen, fibrinogen, growth factors and synthetic peptides.
8. The device of claim 6 wherein the inner bioactive coating is created by plasma treatment.
- 30 9. The device of claim 1 wherein said outer coating is a water-soluble anti-thrombogenic agent.

10. The device of claim 10 wherein the outer coating is selected from the group consisting of acetyl salicylic acid, heparin, coumadin and alnert.

5 11. The device of claim 1 wherein said outer coating further comprises a component that affects the solubility of said outer coating.

12. The device of claim 1 further comprising an overcoating on said outer coating of a component that affects the solubility of said outer coating.

10 13. The device of claim 1 wherein the water-soluble agent dissolves shortly after said vaso-occlusive member is deployed.

14. The device of claim 1 wherein the inner and outer coatings do not affect the shape of said vaso-occlusive member after deployment.  
15

15. A method for treating a vaso-occlusive device comprising  
(a) providing an inner coating for a vaso-occlusive device comprising a bioactive material; and  
(b) providing an outer coating over said inner coating, said outer coating comprising  
20 a water-soluble material.

16. The method of claim 15 where the vaso-occlusive device comprises a metallic element.

25 17. The method of claim 15 where the metallic element comprises a helically wound coil.

18. The method of claim 15 where the helically wound coil comprises a metal selected from gold, rhenium, platinum, palladium, rhodium, ruthenium, stainless steel,  
30 tungsten and alloys thereof.

19. The method of claim 15 wherein the outer coating is selected from the group consisting of acetyl salicylic acid, heparin, coumadin and alnert.

5 20. The method of claim 15 wherein the outer coating further comprises a component which affects the solubility of said outer coating.

21. The product produced by the process of claim 15.



1/1




FIG. 1




FIG. 2

## INTERNATIONAL SEARCH REPORT

International Application No

PC1/US 99/13493

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A61B17/12

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A61B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 94 10936 A (TARGET THERAPEUTICS, INC. ET AL.) 26 May 1994 (1994-05-26) page 5, line 11 - page 6, line 14 page 9, line 19-26 ---	1,15
A	WO 98 04315 A (MICRO THERAPEUTICS, INC.) 5 February 1998 (1998-02-05) page 1, line 35 - page 2, line 29 page 8, line 33 - page 9, line 2 page 10, line 32-36 ---	1,15
A	US 5 700 286 A (TARTAGLIA ET AL.) 23 December 1997 (1997-12-23) column 9, line 5 - column 10, line 13 abstract; figures --- -/--	1,15

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance  
 "E" earlier document but published on or after the international filing date  
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)  
 "O" document referring to an oral disclosure, use, exhibition or other means  
 "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone  
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.  
 "&" document member of the same patent family

Date of the actual completion of the international search

7 September 1999

Date of mailing of the international search report

17/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Giménez Burgos, R

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/13493

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 994 069 A (RITCHART ET AL.) 19 February 1991 (1991-02-19) cited in the application abstract; figures column 5, line 62 - column 6, line 36 ----	1,15
A	DE 196 47 280 A (REUL ET AL.) 23 October 1997 (1997-10-23) abstract; figures -----	

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/13493

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9410936	A	26-05-1994	US 5690666 A	25-11-1997
			AT 165965 T	15-05-1998
			AU 665291 B	21-12-1995
			AU 5362894 A	08-06-1994
			CA 2127713 A	26-05-1994
			DE 9320877 U	08-06-1995
			DE 69318540 D	18-06-1998
			DE 69318540 T	10-09-1998
			EP 0623012 A	09-11-1994
			EP 0824011 A	18-02-1998
			ES 2116472 T	16-07-1998
			JP 2620530 B	18-06-1997
			JP 7508909 T	05-10-1995
			US 5718711 A	17-02-1998
			US 5826587 A	27-10-1998
WO 9804315	A	05-02-1998	US 5823198 A	20-10-1998
			AU 3577297 A	20-02-1998
			AU 3662097 A	20-02-1998
			WO 9804198 A	05-02-1998
US 5700286	A	23-12-1997	US 5637113 A	10-06-1997
			AU 4031295 A	20-06-1996
			CA 2164684 A	14-06-1996
			EP 0716836 A	19-06-1996
			JP 8224297 A	03-09-1996
US 4994069	A	19-02-1991	NONE	
DE 19647280	A	23-10-1997	DE 29518932 U	20-06-1996